## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

## (19) World Intellectual Property Organization International Bureau





(43) International Publication Date 24 February 2005 (24.02.2005)

**PCT** 

## (10) International Publication Number WO 2005/016559 A1

- (51) International Patent Classification<sup>7</sup>: B05D 3/06, B05C 11/08, 5/00, C04B 35/10, C23D 3/00, C23C 26/00
- (21) International Application Number:

PCT/CA2004/001500

- (22) International Filing Date: 17 August 2004 (17.08.2004)
- (25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 60/496,019

19 August 2003 (19.08.2003) US

- (71) Applicant (for all designated States except US): THE UNIVERSITY OF WESTERN ONTARIO [CA/CA]; 2-1151 Richmond Street, London, Ontario N6A 5B8 (CA).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): NIE, Heng-Yong [CA/CA]; 90 Jennifer Road, London, Ontario N5X 3K6 (CA). WALZAK, Mary, Jane [CA/CA]; 937 Apache Road, London, Ontario N5V 2V7 (CA). MCINTYRE, Stewart, N. [CA/CA]; 94 Shavian Blvd., London, Ontario N6G 2P3 (CA).
- (74) Agent: HILL & SCHUMACHER; 87 Falcon Street, Toronto, Ontario M4S 2P4 (CA).


- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF CONTROLLABLE MORPHOLOGY OF SELF-ASSEMBLED MONOLAYERS ON SUBSTRATES



(57) Abstract: Method of controlling the morphology of self-assembled monolayers (SAMS) on substrates having hydrophilic surfaces. The hydrophilic surface is exposed to a fluid having a mixture of molecules which can self-assemble on the hydrophilic surface and hydrophobic molecules for a sufficient length of time so that the molecules which can self-assemble on the hydrophilic surface form a complete self-assembled monolayer. In a particular embodiment octadecylphosphonic acid (OPA) molecules have been self-assembled on oxidized substrates including but not limited to mica, silicon, sapphire, quartz and aluminum by spin-coating a solution containing the octadecylphosphonic acid (OPA) molecules and hydrophobic molecules such as chloroform or trichloroethylene under a controlled relative humidity. Control of the morphology of OPA SAMs is affected by adjusting humidity and the duration of spin-coating. Atomic force microscopy revealed that relative humidity has a profound influence on the morphology of the OPA SAMs formed. When sufficient molecules are applied either consecutively or separately, the final morphology will be a complete monolayer, regardless of the relative humidity.

WO 2005/016559 A1 IIIII